

Zippered right chest pocket



Zippered hand pockets with brushed tricot lining

J0760

Product Features:

- 14.3-oz, 100% polyester bonded with 100% polyester brushed tricot
- 8000mm/800g/m² waterproof/breathability rating
- Full length inner storm flap with comfort chin guard
- Reverse coil zipper at centre front, chest and hand pockets
- Internal storm cuffs

Adult sizes: XS-4XL

Icons/Fabric Features:



Available Colours and PMS Colours

Textile fabric colours are subject to dye lot variation and will not be exact match to print pantone reference

BLACK

GRAVEL



Black 6C



No PMS

Due to the nature of polyester, special care must be taken throughout the decoration process.

J0760 - COAL HARBOUR® Premier Soft Shell Jacket

GARMENT MEASUREMENTS

Size	XS	S	M	L	XL	2XL	3XL	4XL
Chest - <i>Half Measure</i>	20 1/2"	22"	23 1/2"	25"	26 1/2"	28"	30"	32"
Chest - <i>Full Measure</i>	41"	44"	47"	50"	53"	56"	60"	64"
Body Length from HPS (At Back)	26"	27"	28"	29"	30"	31"	31 1/2"	32"
Sleeve Length-CB	34 5/8"	35 1/4"	35 7/8"	36 1/2"	37 1/4"	38"	38 3/4"	39 1/2"

Finished measurements in inches. Refer to "How to Measure" guide for detailed information on measurement instructions.

ADULT General Sizing Guide

Size	XS	S	M	L	XL	2XL	3XL	4XL
Chest	30"-32"	34"-36"	38"-40"	42"-44"	46"-48"	50"-52"	54"-55"	56"-57"
Waist	26"-29"	29"-32"	32"-35"	35"-38"	38"-41"	41"-44"	44"-47"	47"-50"
Sleeve Length-CB	31"-32"	32"-33 1/2"	34"-35"	35"-36"	36"-37"	37"-38"	38"-39"	38 1/2"-39"

COAL HARBOUR®

DECORATING INSTRUCTIONS FOR POLYESTER SOFT SHELL JACKETS

Due to the nature of polyester, special care must be taken throughout the decoration process.

Here are some tips to effectively decorate polyester soft shell products:

- Garment temperature must not exceed 320°F or 160°C. Exceeding this temperature will cause the fabric to shrink, become wavy or cause dye migration.
- Dryer temperature and belt speeds must be changed accordingly for polyester fabric.
- If flashing these garments, do not exceed 1-2 seconds. Anything longer may damage the fabric as stated above.

Screen Printing: These garments require the use of poly inks that cures at a lower temperature. A Dyno Grey base blocker on all colours and a second white base blocker on all dark colours are recommended. Please consult your ink supplier for more information.

- Polyester requires a longer cooling time than cotton. Avoid overlap of garments and screen-print/heat transfer until the garments are cooled. Failure to cool the fabric prior to stacking into a printer's fold may cause the fabric and applied ink to stick together.

Heat Transfers: Poly mark heat transfers need to be created with an anti-migration layer in the design. This process can only be done on white or very light colour shirts. Inks used in printing paper design needs to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.

A test sample run is recommended, especially if you have a large order or if your printer does not specialize in printing on polyester fabrics.