

Essential Water Repellent Soft Shell Jacket

J7610

Product Features:

- 13-oz, 100% polyester with mechanical stretch bonded with 100% polyester brushed tricot
- 20,000mm/5,000g/m² waterproof/breathability rating
- Double needle topstitch throughout

Adult sizes: XS-4XL



Customizable, additional branding opportunity on inside neck



Available Colours and PMS Colours

Textile fabric colours are subject to dye lot variation and will not be exact match to print pantone reference

BLACK



Black 6C

J7610 - Essential Water Repellent Soft Shell Jacket

Garment Measurements


Size	XS	S	M	L	XL	2XL	3XL	4XL
Chest - Half Measure	20"	21 1/2"	23"	24 1/2"	26"	27 1/2"	29 1/2"	31 1/2"
Chest - Full Measure	40"	43"	46"	49"	52"	55"	59"	63"
Body Length from HPS	26 1/2"	27 1/2"	28 1/2"	29 1/2"	30 1/2"	31 1/2"	32"	32 1/2"
Sleeve Length - CB	34 3/4"	35 1/2"	36 1/4"	37"	37 3/4"	38 1/2"	39 1/4"	40"

Finished measurements in inches. Refer to "How to Measure" guide for detailed information on measurement instructions.

Adult General Sizing Guide

Size	XS	S	M	L	XL	2XL	3XL	4XL
Chest	30"-32"	34"-36"	38"-40"	42"-44"	46"-48"	50"-52"	54"-55"	56"-57"
Waist	26"-29"	29"-32"	32"-35"	35"-38"	38"-41"	41"-44"	44"-47"	47"-50"
Sleeve Length - CB	31"-32"	32"-33 1/2"	34"-35"	35"-36"	36"-37"	37"-38"	38"-39"	38 1/2"-39"

Sizing for Branding Area on Inside of Neck



Printing Instructions for Polyester Soft Shell Jackets

Due to the nature of polyester, special care must be taken throughout the decoration process. Here are some tips to effectively decorate our performance products.

Garment temperature must not exceed 320°F or 160°C.

Exceeding this temperature will cause the fabric to shrink, become wavy or cause dye migration.

Dryer temperature and belt speeds must be changed accordingly for polyester fabric.

If flashing these garments, do not exceed 1-2 seconds. Anything longer may damage the fabric as stated above.

SCREEN PRINTING

- These garments require the use of poly inks that cures at a lower temperature. A Dyno Grey base blocker on all colours and a second white base blocker on all dark colours are recommended. Please consult your ink supplier for more information.
- Polyester requires a longer cooling time than cotton. Avoid overlap of garments and screen-print/heat transfer until the garments are cooled. Failure to cool the fabric prior to stacking into a printer's fold may cause the fabric and applied ink to stick together.

HEAT TRANSFERS

- Poly mark heat transfers need to be created with an anti-migration layer in the design. This process can only be done on white or very light colour shirts. Inks used in printing paper design needs to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.

A test sample run is recommended, especially if you have a large order or if your printer does not specialize in printing on performance fabrics.