

Strata Tech Soft Shell Ladies' Jacket



Available Colours and PMS Colours

Textile fabric colours are subject to dye lot variation and will not be exact match to print pantone reference



DF7662L



Product Features:

- 14.7-oz, 91/9 polyester/spandex bonded with 100% polyester micro fleece
- 5000mm/2000g/m² waterproof/breathability rating
- Articulated sleeves
- Drawcord and toggles at hem
- Reflective **D**RYFRAME logo on bottom left hem and storm flap
- Detachable carabiner keychain located in left hand pocket

Ladies' sizes: XS-4XL

Icons/Fabric Features:



WARMTH RATING	MILD	WARM	WARMER	WARMEST		
WATER PROTECTION	WATER F	ESISTANT	WATERPROOF			
WATERPROOF RATING	5000mm	BREATHA	BILITY RATING	2000g/m² -		
INTERIOR	ANTI-PILL MICRO FLEECE					

DF7662L - DRYFRAME® Strata Tech Soft Shell Ladies' Jacket

GARMENT MEASUREMENTS								
Size	XS	S	м	L	XL	2XL	3XL	4XL
Chest - Half Measure	19"	20"	21"	22 1/2"	24"	25 1/2"	27 1/2"	29 1/2"
Chest - Full Measure	38"	40"	42"	45"	48"	51"	55"	59"
Body Length from HPS (At Front)	25 1/2"	26"	26 1/2"	27 1/2"	28 1/2"	29 1/2"	30"	30 1/2"
Sleeve Length-CB	33"	33 1/2"	34"	34 1/2"	35"	35 1/2"	36"	36 1/2"

Finished measurements in inches. Refer to "How to Measure" guide for detailed information on measurement instructions.

LADIES' General Sizing Guide								
Size	XS	S	м	L	XL	2XL	3XL	4XL
Numeric Size	2	4-6	8-10	12-14	16	18-20	22	24
Bust	32"-34"	35"-36"	37"-38"	39"-41"	42"-44"	45"-47"	48"-51"	52"-55"
Waist	24"-25"	26"-27"	28"-30"	30"-32"	33"-35"	36"-38"	40"-42"	42"-44"
Hip	33"-35"	35"-37"	37"-39"	39"-41"	42"-44"	45"-47"	48"-50"	50"-52"
Sleeve Length-CB	30"-30 1/2"	30 1/2"-31"	31 1/2"-32"	32 1/2"-33"	33 1/2"-34"	34"-34 1/2"	34 1/2"-35"	34 1/2"-35"

DRYFRAME CONTROL YOUR CLIMATE®

DECORATING INSTRUCTIONS FOR POLYESTER FABRICS

Due to the nature of polyester, special care must be taken throughout the decoration process. Here are some tips to effectively decorate our performance products.

Garment temperature must not exceed 320°F or 160°C. Exceeding this temperature will cause the fabric to shrink, become wavy
or cause dye migration.

• Dryer temperature and belt speeds must be changed accordingly for polyester fabric.

• If flashing these garments, do not exceed 1-2 seconds. Anything longer may damage the fabric as stated above.

• Screen Printing: These garments require the use of poly inks that cures at a lower temperature. A Dyno Grey base blocker on all colours and a second white base blocker on all dark colours are recommended. Please consult your ink supplier for more information.

• Polyester requires a longer cooling time than cotton. Avoid overlap of garments and screen-print/heat transfer until the garments are cooled. Failure to cool the fabric prior to stacking into a printer's fold may cause the fabric and applied ink to stick together.

• Heat Transfers: Poly mark heat transfers need to be created with an anti-migration layer in the design. This process can only be done on white or very light colour shirts. Inks used in printing paper design needs to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.

• Sublimation Printing: As noted for the poly mark heat transfers, this process can only be done on white or very light colour shirts. Inks used in printing paper design needs to be darker than the base fabric or colour will migrate with the fabric colour resulting in a bleeding effect.

• If you heat press these garments, you must adjust the time, temperature and pressure. Failure to do so may damage the fabric as stated above.

• A test sample run is recommended, especially if you have a large order or if your printer does not specialize in printing on performance fabrics.